

Preliminary data sheet

LUVOSINT X92A-1

Ester based thermoplastic polyurethane TPU
Powder, natural color

Physical Properties	Test Method	Specimen	Units	Typical Value	
Specific Gravity	ISO 1183	Sintered part	g/cm ³	1.2	
Water Absorption	23 °C, 24 h		%	< 0.5	
Melt Volume Rate	MVR 190 °C/2.16 kg	Power	cm ³ /10 min	18	
Glass Transition Temp	ISO 6721-1		°C	-13.6	
Mechanical Properties					
at 23 °C/ 50 % rh (according to build orientation)					
Shore Hardness A	ISO 868	Sintered part	-	88	
Flexural Modulus 20°C	1 Hz, 2 °C/min	ISO 6721-1	Sintered part	MPa	27
Flexural Modulus 60°C	1 Hz, 2 °C/min	ISO 6721-1	Sintered part	MPa	72
Tensile Strength (x-direction)	DIN 53504	Sintered S1-bar	MPa	20	
Tensile Strength (z-direction)	DIN 53504	Sintered S1-bar	MPa	15	
Elongation (x-direction)	DIN 53504	Sintered S1-bar	%	520	
Elongation (z-direction)	DIN 53504	Sintered S1-bar	%	500	
Abrasion Resistance (x-direction)	ISO 4649	Sintered part	mm ³	31	
Abrasion Resistance (z-direction)	ISO 4649	Sintered part	mm ³	28	
Compression Strength (x-direction)	ISO 604	Type A	MPa	33	
Compression Strength (z-direction)	ISO 604	Type A	MPa	40	
Compression Modulus (x-direction)	ISO 604	Type B	MPa	15	
Compression Modulus (z-direction)	ISO 604	Type B	MPa	20	
Poisson ratio (Hencky)	0.2 mm/s			0.45	
Thermal Properties					
Vicat-softening Temperature	VST A	ISO 306	MPTS ISO 3167 A	°C	90
Melting Temperature		ISO 11357		°C	160
Powder Properties					
x10	Laser diff.		µm	20	
x50	Laser diff.		µm	50	
x90	Laser diff.		µm	105	
Bulk Density			g/cm ³	457	

7859 19 06 14

Application Examples

Powder for laser sintering (additive manufacturing). Elastic parts with high strength and high abrasive resistance for shoe and sports industry, pipes, sealings, prosthetics and many more applications.

Preliminary data sheet

LUVOSINT X92A-1

Ester based thermoplastic polyurethane TPU
Powder, natural color

Recommended Processing Instructions

General

In general LUVOSINT X92A-1 can be processed on conventional lasersinter machines while observing the usual technical guidelines. In contrast to conventional polyamide powders relatively low temperatures in the process chamber should be used here. At higher temperatures above 100 °C powder flowability and process stability will decrease. Aspiration is recommended due to formation of fume.

Predrying

No predrying necessary.
 The powder should be de-agglomerated by using a screening process (250 microns sieve opening) before processing.

Processing Parameters

Due to the large variety of machines and part geometries given process parameters can only be seen as an orientation.

Please use material data base of Polystyrene and change process parameters as follows:

Process Temperature	°C	100
Piston Heater	°C	85
Scan Speed	mm/s	4000
Hatch Distance	mm	0.20
Layer Thickness	mm	0.15
Laser Power	W	40

Delivery Form & Storage

The material will be delivered as 25 kg boxes on pallets.
 Preferably storage should be effected in dry and normally temperatured rooms.

Headquarters

Lehmann & Voss & Co.
 Alsterufer 19
 20354 Hamburg
 Germany
 Tel +49 40 44 197-250
 Fax +49 40 44 197-487
 Email: luvo.com@lehvoss.de

Americas

LEHVOSS North America, LLC
 185 South Broad Street
 Pawcatuck, CT 06379
 USA
 Tel +1-855-681-3226
 Fax +1 860 495 2047
 Email info@lehvossllc.com

Asia

LEHVOSS (Shanghai) Chemical Trading Co., Ltd.
 Unit 1590, L'Avenue,
 99 Xianxia Road, Changning District,
 Shanghai 200051
 China
 Tel +86 21 60577297
 Email info@lehvoss.cn

Asia

LEPS Compounds Korea
 130B-8-L, 695-7 Gojan-dong,
 Namdong-gu
 Incheon,, 405-310
 Korea
 Tel +82 10 3775 6567
 Email info@lehvoss.cn

Lehmann & Voss & Co.



Any recommendations made for use of Seller's materials are made to the best of Seller's knowledge and are based upon prior tests and experience of the Seller believed to be reliable; however, Seller does not guarantee the results to be obtained and all such recommendations are non-binding – also with regard to the protection of third party's rights –, do not constitute any representation and do not affect in any way Buyer's obligation to examine and/or test the Seller's our goods with regard to their suitability for his Buyer's purposes. No information given by the Seller is to be construed in any way as a guarantee regarding characteristics or duration of use, unless such information has been explicitly given as a guarantee.